

PAROC Marine Mat 35 AluCoat

PAROC Marine Mat 35 AluCoat is a non-combustible stone wool mat with glass-fiber scrim reinforced aluminium foil facing for thermal insulation on ships.



Product datasheet

19.2.2025

Dimensions	Width x Length (mm)	Thickness (mm)
	500/600/900/1000 x 8000	30
	500/600/900/1000 x 7000	40
	500/600/900/1000 x 7000	50
	500/600/900/1000 x 7000	60
	500/600/900/1000 x 5000	70
	500/600/900/1000 x 5000	80
	500/600/900/1000 x 4000	100
	500/600/900/1000 x 3000	120

Nominal Density
35 kg/m³
Plastic packs on pallet

Product characteristics	Fire Classification (IMO 2010 FTP Code Annex 1)		Type-Examination (Module B) certificate(s)					
	Part 1, Non-combustibility		74480/A1 MED, 74465/A1 UK					
	Part 5, Low Flame-Spread characteristics		74479/A1 MED, 74467/A1 UK					
	Quality system		Surveillance (Module D) certificate(s)					
	MED		SMS.MED2.D/93834/A.3					
	UK		SMS.UK.D/93834/A.2					
	Water absorption short term (EN 29767)		≤ 1 kg/m²					
	Thermal conductivity		See table below					
	Mean temperature (°C)	10						
	Thermal conductivity (W/mK)	0.035						

Fire Properties
PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Environmental Properties

PAROC stone wool products are made from clean, natural material. They are environmentally friendly throughout their lifecycle, causing no harm to nature during or after their use. Stone wool does not contain any ingredients or chemicals that prevent or impede recycling.

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Paroc makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Paroc reserves the right to modify this document without prior notice. PAROC is a registered trademark of Paroc Group Oy. This data sheet is valid in following countries: International.